

## Finishing putty FEIN

### Description:

Two-components micro polyester putty to be used to even the scratches which appear after processing the filling putty. This product is also used to even small scratches on lacquered surfaces without the necessity of using filling putties. It is easy to apply and spread on the surface without leaving any pores. It is marked by good elasticity, it can be easily processed and has good adhesion also in contact with galvanized steel. After grinding it results in a very smooth surface. It harmonizes with most paints and lacquers available on the market.

### It can be used on the following surfaces:

- Steel
- Galvanized steel
- Aluminium
- Two-components acryl fillers
- Old lacquer coats
- Polyester laminates

**Attention!** Do not apply directly on wash primers, one-component acryl or nitrocellulose products.

### FEIN putty can be over-painted with:

- Polyester spray putty UNI-SPRAY
- Acryl fillers by RANAL

### Mixing ratio:

FEIN putty	100 parts by weight
Hardener	2 – 2,5 parts by weight

**Attention!** Avoid overdosing the hardener. In consequence, discolouring of the lacquer may occur. Do not pour the product mixed with hardener back to the package with unused putty.

### Instruction for use:

Mix the components carefully according to mixing ratio. Apply on ground, cleaned, and degreased surface. Apply with a spatula coats thick up to 4-5 mm. Between the applications of the coats, wait for some time in order to harden the previous coat. Aluminium surface should be previously matted with nonwoven fabric. If wet processed, the coat of the putty should be carefully dried.

**Attention!** Do not apply in the temperature below 10°C.

### Pot life:

About 4 - 6 minutes in the temperature of 20°C.

**Drying time:**

About 30 minutes in the temperature of 20°C.

Drying time can be reduced by keeping for about 10 minutes the temperature of 60°C.

**Recommended gradation of paper:**

Preliminary grinding – P180 – P240

Final grinding - P240 - P320

**Colour:**

Light grey

**Tools cleaning:**

Acryl thinner or nitro.

**Storage:**

To be stored in dry and cool place, away from the sources of light and heat. Avoid sun exposure. Storage time of the product in the original package in the temperature 20°C is equal to: In case of putty – 12 months, and in case of hardener – 18 months.

**Health and safety recommendations:**

Apply safety data sheet of the particular product.

**Packaging:**

Art.Nr	Capacity, kg:	Package, pieces:	Weight of the carton, kg
00303-3	0,25	30	9,50
00301-3	0,5	16	9,70
00302-3	1,7	6	11,60

This information is based on careful, laboratory research and our long-standing experience. Strong market position does not absolve us from constant control of the quality of our products. However, we are not responsible for the final results after incorrect use of the product.

RANAL Sp. z o.o.